








CARATTERISTICHE TECNICHE BICOTTURA ISO 13006 - BIII GL (E > 10%)
DOUBLE FIRING TECHNICAL CHARACTERISTICS ISO 13006 - BIII GL (E > 10%)
DONNEES TECHNIQUES DE LA BICUISSON ISO 13006 - BIII GL (E > 10%)
TECHNISCHE EIGENSCHAFTEN DER ZWEIBRANDFLIESEN ISO 13006 - BIII GL (E > 10%)
CARACTERÍSTICAS TÉCNICAS DE LA BICOCCIÓN ISO 13006 - BIII GL (E > 10%)

CARATTERISTICA SPECIFICATION CARACTERISTIQUE EIGENSCHAFT CARACTERÍSTICA	NORMA STANDARD APPLICABLE STANDARD NORME STANDARD NORM NORMA ESTANDAR	VALORE PRESCRITTO PRESCRIBED VALUE VALEUR PRESCRITE VORGESCHRIEBENER WERT VALOR REQUERIDO	VALORE MEDIO BICOTTURA IMOLA CERAMICA IMOLA CERAMICA DOUBLE FIRING AVERAGE VALUE VALEUR MOYENNE BICUISSON IMOLA CERAMICA DURCHSCHNITTLICHER WERT ZWEIBRANDFLIESEN IMOLA CERAMICA VALOR MEDIO BICOCCIÓN IMOLA CERAMICA
 DIMENSIONI E ASPETTO DIMENSIONS AND APPEARANCE DIMENSIONS ET ASPECT MAßE UND AUSSEHEN DIMENSIONES Y ASPECTO	ISO 10545-2	CONFORME COMPLIANT CONFORME ERFÜLLT CONFORME	CONFORME COMPLIANT CONFORME ERFÜLLT CONFORME
 ASSORBIMENTO D'ACQUA WATER ABSORPTION ABSORPTION D'EAU WASSERAUFNAHME ABSORCIÓN DE AGUA	ISO 10545-3	> 10%	> 10%
 RESISTENZA A FLESSIONE FLEXURAL RESISTANCE RESISTANCE A LA FLEXION BIEGEFESTIGKEIT RESISTENCIA A LA FLEXIÓN	ISO 10545-4	Spessore - Thickness Epaisseur - Stärke - Espesor > 7,5 mm: $\geq 12 \text{ N/mm}^2$ Spessore - Thickness Epaisseur - Stärke - Espesor $\leq 7,5 \text{ mm}$: $\geq 15 \text{ N/mm}^2$	$17 \text{ N/mm}^2 = 173 \text{ Kg/cm}^2$
FORZA DI ROTTURA MODULS OF RUPTURE CHARGE DE RUPTURE BRUCHLAST CARGA DE RUPTURA		Spessore - Thickness Epaisseur - Stärke - Espesor $\geq 7,5 \text{ mm}$: $\geq 600 \text{ N}$ Spessore - Thickness Epaisseur - Stärke - Espesor $< 7,5 \text{ mm}$: $\geq 200 \text{ N}$	CONFORME COMPLIANT CONFORME ERFÜLLT CONFORME
DUREZZA MOHS SCRATCH RESISTANCE DURETE SUPERFICIELLE OBERFLÄCHENRITZHÄRTE NACH MOHS DUREZA SUPERFICIAL	EN 101	$\geq 3 \text{ Mohs}$	CONFORME COMPLIANT CONFORME ERFÜLLT CONFORME
 COEFFICIENTE DILATAZIONE TERMICA LINEARE (A) LINEAR EXPANSION THERMIC COEFFICIENT COEFF. DILATATION THERMIQUE LINEIQUE LINEARER TERMISCHEAUSDEHNUNGSKOEFFIZIENT COEF. DILATACIÓN TERMICA LINEAL	ISO 10545-8	$\leq 9 \times 10^{-6} \text{ } ^\circ\text{C}^{-1}$	$7 \times 10^{-6} \text{ } ^\circ\text{C}^{-1}$
 RESISTENZA AGLI SBALZI TERMICI RESISTANCE TO SUDDEN TEMPERATURE CHANGES RESISTANCE AUX CHOCS TERMIQUES TEMPERATURWECHSELBESTÄNDIGKEIT RESISTENCIA A LAS VARIACIONES TERMICAS	ISO 10545-9	METODO DISPONIBILE AVAILABLE ON REQUEST METHODE DISPONIBLE VERFÜGBARES VERFAHREN TEST DISPONIBILE	RESISTE RESISTANT RESISTANT BESTÄNDIG RESISTE
RESISTENZA AL CAVILLO CRAZING RESISTANCE RESISTANCE AU TRESSAILLAGE GLASURRISSÉ-BESTÄNDIGKEIT RESISTENCIA AL CUARTEADO	ISO 10545-11	RICHIESTA ALWAYS TESTED EXIGEE NOTWENDIG NECESARIA	RESISTE RESISTANT RESISTANT BESTÄNDIG RESISTE
 RESISTENZA AI PRODOTTI CHIMICI CHEMICAL RESISTANCE RESISTANCE CHIMIQUE CHEMISCHE BESTÄNDIGKEIT RESISTENCIA QUIMICA	ISO 10545-13	METODO DISPONIBILE AVAILABLE ON REQUEST METHODE DISPONIBLE VERFÜGBARES VERFAHREN TEST DISPONIBILE	CONFORME COMPLIANT CONFORME ERFÜLLT CONFORME
 RESISTENZA ALLE MACCHIE STAIN RESISTANCE RESISTANCE AUX TACHES FLECKBESTÄNDIGKEIT RESISTENCIA A LAS MANCHAS	ISO 10545-14	≥ 3	RESISTE RESISTANT RESISTANT BESTÄNDIG RESISTE